



NOTES

1. PRECAST CONCRETE TYPE 2 4000 P.S.I.
2. "RAM-NEK OR EQUAL AT ALL RISER JOINTS(1/2" THICK W/WIDTH AT LEAST 1/2 THE WALL THICKNESS) W/GROUT INSIDE AND OUTSIDE.
3. ALL OPENINGS SHALL BE SEALED WITH A WATERPROOF NON-SHRINKING GROUT.
4. FLOW CHANNELS SHALL BE FIELD CONSTRUCTED TO DIRECT FLOW STREAM.
5. LIFT HOLES ARE NOT PERMITTED FURNISH LIFTING CABLES.
6. ALL PIPE HOLES SHALL BE PRECAST OR CORE-DRILLED.
7. RUBBER BOOT MUST BE USED WITH ALL PIPE CONNECTIONS.
8. INSIDE DROPS SHALL NOT BE ALLOWED OR DETERMIND BY ENGINEER
9. MANHOLES SHALL BE COATED INSIDE AND OUT WITH TWO COATS OF COAL TAR EPOXY OR CS-55 WATER BASED CONCRETE COATING, MIN. 8 MILS PER COAT.

STANDARD MANHOLE DETAIL